

DU PONT-MITSUI POLYCHEMICALS CO.,LTD.

Shiodome City Center
5-2, Higashi-Shimbashi 1-chome
Minato-ku, Tokyo 105-7117, Japan

TEL: 81-3-6253-4006
FAX: 81-3-6253-4262

EVAFLEX® EV45X

Property	Test Method	Units	EV45X
VA Content	JIS K7192	wt%	46
MFR	JIS K7210	g/10min	100
Density	JIS K7112	Kg/m ³	970
Tensile Strength	JIS K7161	MPa	0.5
Elongation	JIS K7161	%	2,600
Stiffness	JIS K7106	MPa	< 10
Hardness(Shore A)	JIS K7215	Degree	16
Vicat Softening Point	JIS K7206	°C	< 30
Melting Point	JIS K7121	°C	—

The data shown are typical values and should not be used for specifications.



DU PONT-MITSUI POLYCHEMICALS CO.,LTD.